

PRODUCT DATA

3 03 39 00 Concrete Curing

Description

Kure-N-Seal 25 LV is a transparent, low-viscosity, 25% solids, VOCcompliant, solvent-based acrylic curing, sealing and dustproofing compound designed for better application at cool temperatures. Its semi-gloss finish provides good UV resistance and gloss retention.

Yield

Ft²/gallon per coat (m²/L):

Curing only:

200 - 400 (4.9 - 9.8) Dustproofing and sealing:

1st coat: 200 - 400 (4.9 - 9.8) 2nd coat: 400 - 600 (9.8 - 14.6)

Renovating, dustproofing, and sealing: 200 - 300 (4.9 - 7.3)

Under mastic floor adhesives: 400 - 600 (9.8 - 14.6)

Coverage rates listed are approximations. Coverage varies with texture and porosity of surface; actual surface profile will determine exact coverage rate.

KURE-N-SEAL[®] 25 LV

Low-viscosity, transparent, solvent-based, acrylic curing, sealing and dustproofing compound

Features

Features	Benefits
Curing compound	Efficiently retains moisture for freshly placed concrete; ensures proper strength development; minimizes shrinkage cracking
Low viscosity	Provides better application at cool temperatures
Sealer and dustproofer	Makes surfaces easier to clean and maintain
Semi-gloss appearance	Surfaces look newer and brighter
Abrasion resistant	Withstands foot traffic; provides extended wear
Compatible with a variety of adhesives	Can be tiled or carpeted over
25% solids by weight	Economical, VOC compliant

Packaging

Kure-N-Seal 25 LV: 5 gallon (18.9 L) pails 55 gallon (208 L) drums

Color

Amber; dries clear

Shelf Life

18 months when properly stored

Storage

Store in unopened containers in a cool, clean, dry area. Keep Kure-N-Seal 25 LV from freezing in the container; do not store below 35° F (2° C).

Where to Use

LOCATION

- Interior and exterior
- Horizontal and vertical

SUBSTRATE

- Freshly placed and finished concrete
- Aged concrete
- Exposed aggregate •
- Brick •
- Terrazzo



Technical Data

Composition

Kure-N-Seal 25 LV is an acrylic polymer resin in a solvent carrier.

Compliances

- Kure-N-Seal 25 LV is recommended for use on Class 1, 2, 3 and 4 concrete floors as classified in Table 1.1, ACI Standard 302
- ASTM C 309, Type 1, Class A
- ASTM C 1315, Type I, Class A (per AIM regulations)
- Corps of Engineers CRD-C304,
- Type I (or ID), Class A or B AASHTO M-148
- USDA compliant for use in meat and poultry areas, when fully cured

Test Data

loot bata			
PROPERTY	RESULTS	TEST METHODS	
Moisture retention, kg/m ² applied at 300 ft²/gal Kure-N-Seal 25 LV Test requirement	0.38 < 0.4	ASTM C 156	
Drying time, hrs	< 4	ASTM C 1315	
Solids, %	25	ASTM C 1644	
Flashpoint, ° F (° C)	> 109 (> 42)	ASTM D 56	
Acid and alkali resistance, at 1 and 16 hours	No effect observed	ASTM D 1308	
UV light resistance	Membrane lighter than Gardner color 3	ASTM G 53	
Adhesion of tile cement, psi	> 165	ASTM C 1315	
Test results are averages obtained under la	aboratory conditions. Beasonable variations	can be expected	

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

How to Apply

Surface Preparation

NEWLY PLACED CONCRETE

- 1. Surface must be sound and properly finished.
- 2. Surface is application ready when damp, but not wet, and it can no longer be marred by foot traffic.

NEWLY CURED BARE CONCRETE

1. Level any gouges.

2. Remove all dirt, dust, oil, grease, asphalt and foreign matter. Clean with caustics and detergents as required. Citrus Degreaser is excellent for removing oil stains and many curing compounds (see Form No. 1017985).

3. Rinse thoroughly and allow to dry. Kure-N-Seal 25 LV may be applied to damp but not wet surfaces.

AGED CONCRETE

1. Restore surface to soundness by patching, grouting and filling cracks or holes.

2. Surface must also be free of any dust, dirt and other foreign matter.

3. Use power tools or strippers to remove any incompatible sealers or coatings.

4. Clean as required, following procedure under "Newly cured bare concrete."

Application

1. Stir Kure-N-Seal 25 LV thoroughly before using.

2. Apply a continuous, uniform film by low-pressure spray only, shortnap roller or lamb's wool applicator. For best results, use a Hudson® Industro® or equivalent canister curing compound sprayer. Use a tip size of 0.8004 for water-based or waterborne products. Use a tip size of 0.11010 for solvent-based products.

3. For curing, apply first coat evenly and uniformly as soon as possible after final finishing. Apply second coat when all construction is completed and structure is ready for occupancy.

4. To seal and dustproof, 2 coats must be applied. For sealing new and aged concrete, apply both coats full strength.

Clean Up

Clean tools and equipment with Reducer 990 immediately after use and while Kure-N-Seal 25 LV is still wet.

Drying Time

At 65 to 85° F (18 to 29° C) at 50% relative humidity. High humidity will increase drying times. Light foot traffic or between coats: 3 hours Normal traffic: overnight

Maximum hardness : 7 days

Maintenance

Routinely sweep and wash with conventional cleaners and detergents. Remove all abrasive grit and wipe up corrosive spills as soon as possible. Inspect membrane periodically for wear or breaks and gouges in the surface. If required, areas can be renovated by reapplying Kure-N-Seal 25 LV to regain original gloss and protection.

For Best Performance

- Kure-N-Seal 25 LV may settle and must be stirred thoroughly before and during application.
- Do not thin.
- Keep away from heat and open flame.
- Application not recommended when surface temperature exceeds 120° F (49° C).
- If Kure-N-Seal 25 LV is to be applied in or near areas containing foodstuffs, they should be removed before application; do not return foodstuffs until Kure-N-Seal 25 LV has fully dried and all solvent vapors have dissipated.
- Heating Ventilation Air Conditioning (HVAC) units may draw solvent vapors into occupied building interiors. Solvent vapors can be irritating. Do not apply Kure-N-Seal 25 LV in or around buildings occupied by nonconstruction personnel without consulting building management and taking appropriate precautions. Use only with adequate ventilation and with a minimum of 6 air changes per hour.

- Do not apply Kure-N-Seal 25 LV to the interfacing of channels to be caulked with elastomeric sealants; avoid sealant adhesion problems by masking.
- Do not use on surfaces to receive concrete overlays or additional toppings or coatings.
- Not recommended as a release agent or where other sealers or treatments are to be later applied.
- Kure-N-Seal 25 LV should not be used in areas requiring resistance to solvents such as gasoline, diesel fuel or paint thinners.
- Avoid excess moisture until material is fully cured.
- Although Kure-N-Seal 25 LV is compatible with a variety of tile, carpet and floor covering adhesives, a test application is always recommended.
- Kure-N-Seal 25 LV can be applied to colored concrete or dry-shake hardeners, but mottling may occur. Kure-N-Seal 25 LV will highlight imperfections and may darken the final appearance of the concrete surface.
- Kure-N-Seal 25 LV is considered a light-duty sealer; may rubber burn when subjected to forklift or other wheeled traffic.
- Mechanical methods are recommended for removing Kure-N-Seal 25 LV.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user.
 Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

KURE-N-SEAL 25 LV

Caution

Kure-N-Seal 25 LV contains solvent naphtha (petroleum), light aromatic, 1, 2, 4, trimethyl benzene, xylene, Stoddard solvent and ethyl benzene.

Risks

Combustible liquid and vapor. May cause skin and eye irritation. May cause dermatitis and allergic responses. Inhalation of vapors may cause irritation and intoxication with headaches, dizziness and nausea. Ingestion may cause irritation. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Precautions

READ MSDS AND TECHNICAL DATA GUIDE BEFORE USING. DO NOT USE UNTIL ALL BYSTANDERS HAVE BEEN WARNED OF PRODUCT HAZARDS. KEEP AWAY FROM HEAT, FLAME AND SOURCES OF IGNITION. Vapors are heavier than air. DO NOT cut or weld on or near empty container. Empty container may contain explosive vapors or hazardous residues. Keep container closed. Use only with adequate ventilation. Prevent contact with eyes, skin and clothing. Wash thoroughly after handling. DO NOT breathe vapors. Use impervious gloves, eye protection and if the TLV is exceeded or product used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations. All label warnings must be observed until container is commercially cleaned or reconditioned. KEEP OUT OF THE REACH OF CHILDREN.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK IMMEDIATE MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

5.02 lbs/gal or 601 g/L, less water and exempt solvents.

For medical emergencies only, call ChemTrec (1-800-424-9300).

BASF Corporation Building Systems

889 Valley Park Drive Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517 **Technical Service** 800-243-6739 LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replace monter of them. BASF MARES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, NOLDING WARRANTES OF FITNESS OF A PARTICULAR PURPOSE OR MERICHANTABILITY, RESPECTIVE ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such writine notice or after the specified time interval. User stall determine the subability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must be assume or the BASF Technical Manager.