

PRODUCT DATA

3 03 39 00 **Concrete Curing**

# KURE-N-SEAL™ 30

Transparent, acrylic, solvent-based and high-gloss curing, sealing, and dustproofing compound

### Description

Kure-N-Seal™ 30 is a transparent, 30% solids, solvent-based, acrylic curing membrane. Apply it to damp or dry surfaces to provide a high-gloss finish.

### Yield

For curing only, 1 coat may be sufficient; 2 coats, however, will give best results. To seal and dustproof, 2 coats are required.

Ft<sup>2</sup>/gallon (m<sup>2</sup>/L) per coat:

Curing only:

200 – 400 (4.9 – 9.8)

Second coat (dustproofing and sealing)  
400 – 600 (9.8 – 14.7)

Renovating, dustproofing, and sealing:  
200 – 300 (4.9 – 7.4)

Under mastic-type floor adhesives:  
400 – 600 (9.8 – 14.7)

Coverage varies with application method, texture, and porosity of surface.

### Features

- Compliant with AIM regulations
- 30% solids by weight
- Curing compound
- Sealer and dustproofer
- Abrasion resistant
- Reduced fluid penetration
- Compatible with a variety of adhesives

### Benefits

- Offers a range of temperature applications
- Provides a high gloss finish
- Efficiently retains moisture for freshly placed concrete; ensures proper strength development; minimizes shrinkage cracking
- Makes surfaces easier to clean and maintain
- Extends wear
- Increases stain resistance of concrete
- Can be tiled or carpeted over

### Packaging

Kure-N-Seal™ 30:  
5 gallon pails (18.93 L)  
55 gallon drums (208 L)  
Reducer 990:  
1 gallon (3.8 L) pails

### Color

Transparent

### Shelf Life

18 months when properly stored.

### Storage

Store in unopened containers in cool, clean, dry area.

### Where to Use

#### APPLICATION

- Offices

- Warehouses
- Commercial buildings

#### LOCATION

- Interior or exterior

#### SUBSTRATE

- Freshly placed concrete
- Finished concrete
- Aged concrete

### How to Apply

#### Surface Preparation

NEWLY PLACED CONCRETE

## Technical Data

### Composition

Kure-N-Seal™ 30 is an acrylic polymer in a solvent carrier.

### Compliances

- Recommended for concrete floors as defined in Table 1.1, ACI Standard 302.1R
- Federal Specification TT-C-800A
- AASHTO M-148
- ASTM C 1315, Type 1, Class B (per AIM regulations)
- USDA compliant for use in meat and poultry areas when fully cured
- Corps of Engineers CRD-C-304, Type 1
- ASTM C 309, Type 1, Class A and B

### Typical properties

PROPERTY	VALUE
Solids content, % by weight	30

### Test Data

PROPERTY	RESULTS	TEST METHODS
<b>Moisture retention, kg/m<sup>2</sup></b> (applied at 200 ft <sup>2</sup> /gal)		ASTM C 309
Kure-N-Seal™ 30	0.21	
Test requirement	≤ 0.55	
<b>Moisture retention, kg/m<sup>2</sup></b> (applied at 300 ft <sup>2</sup> /gal)		ASTM C 156
Kure-N-Seal™ 30	0.32	
Test requirement	< 0.4	

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

1. Surface must be sound and properly finished.
2. Surface is application ready when damp but not wet, and it can no longer be marred by foot traffic.

#### NEWLY CURED BARE CONCRETE

1. Level any gouges.
2. Remove all dirt, dust, oil, grease, asphalt and foreign matter. Clean with caustics and detergents as required. Citrus Degreaser is excellent for removing oil stains and many curing compounds (see Form No. 1017985).
3. Rinse thoroughly and allow to dry so that surface is no more than damp and never wet.

#### AGED CONCRETE

1. Patch, grout and fill cracks and holes.
2. Surface must also be free of any dust, dirt, and other foreign matter. Remove any incompatible sealers or coatings. Clean as described under "Newly cured concrete."

### Application

1. Stir Kure-N-Seal™ 30 thoroughly before using.
2. Apply a continuous, uniform film by an airless

sprayer with a tip size of 0.519, short-nap roller or lamb's wool applicator. Hand held sprayers are not recommended.

3. For curing, apply evenly and uniformly after final finishing. Apply second coat when all trades have finished and structure is ready for occupancy.
4. To seal and dustproof, 2 coats are required. Apply the second application when all trades are completed and site is ready for occupancy.

### Drying Time

At 65 to 85° F (18 to 29° C) at 50% relative humidity.

Light foot traffic or between coats: 4 hours

Normal traffic: overnight

Maximum hardness: 7 days

### Maintenance

1. Routinely sweep and wash floors with conventional cleaners and detergents.
2. Remove all abrasive grit and wipe up corrosive spills as soon as possible.
3. Inspect application periodically for wear.
4. Renovate by reapplying Kure-N-Seal™ 30 to regain original gloss and protection.

### Clean Up

Clean tools and equipment with Reducer 990 immediately after use and while Kure-N-Seal™ 30 is still wet.

## For Best Performance

- Do not thin.
- Keep away from heat and open flame.
- Application not recommended when surface temperatures exceed 120° F (49° C).
- For best appearance and performance, apply uniformly and at recommended coverage rates.
- If Kure-N-Seal™ 30 is to be applied in or near areas containing foodstuffs, they should be removed before application; do not return foodstuffs until Kure-N-Seal™ 30 has fully dried and all solvent vapors have dissipated.
- Heating Ventilation Air Conditioning (HVAC) units may draw solvent vapors into occupied building interiors. Solvent vapors can be irritating. Do not apply Kure-N-Seal™ 30 in or around buildings occupied by nonconstruction personnel without consulting building management and taking appropriate precautions. Use only with adequate ventilation and with a minimum of 6 air changes per hour.
- Do not apply Kure-N-Seal™ 30 to joint faces to be caulked with elastomeric sealants; protect joint faces by masking.
- Not intended for surfaces to receive concrete overlays or additional toppings, coatings, sealers or ceramic tile (without proper surface preparation).
- Not recommended as a release agent.
- Do not use in areas that require resistance to solvents.
- Although Kure-N-Seal™ 30 is compatible with a variety of carpet, vinyl tile and floor covering adhesives, always conduct a test application beforehand.
- Kure-N-Seal™ 30 will highlight imperfections and may darken the final appearance of the concrete surface.
- Kure-N-Seal™ 30 can be applied to colored concrete or dry shake hardeners, but mottling may occur.
- Kure-N-Seal™ 30 is considered a light-duty sealer; may rubber burn when subjected to forklift or other wheeled traffic.
- Mechanical methods are recommended for removing Kure-N-Seal™ 30.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and MSDS are being used;

call Customer Service (1-800-433-9517) to verify the most current versions.

- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

## Health and Safety

KURE-N-SEAL™ 30

### Caution

Kure-N-Seal™ 30 contains Solvent naphtha (petroleum), light aromatic; 1, 2, 4 trimethyl benzene; xylene; Cumene and Styrene.

### Risks

Combustible liquid and vapor. May cause skin and eye irritation. May cause dermatitis and allergic responses. Inhalation of vapors may cause irritation and intoxication with headaches, dizziness and nausea. Ingestion may cause irritation. May be absorbed through skin. Repeated or prolonged exposure increases the risk of absorption. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

### Precautions

READ MSDS AND TECHNICAL DATA GUIDE BEFORE USING. DO NOT USE UNTIL ALL BYSTANDERS HAVE BEEN WARNED OF PRODUCT HAZARDS. KEEP OUT OF THE REACH OF CHILDREN. KEEP AWAY FROM HEAT, FLAME AND SOURCES OF IGNITION. Vapors are heavier than air. DO NOT cut or weld on or near empty container. Empty container may contain explosive vapors or hazardous residues. Keep container closed. Use only with adequate ventilation. Prevent contact with eyes, skin and clothing. Wash thoroughly after handling. DO NOT breathe vapors. Use impervious gloves, eye protection and if the TLV is exceeded or product is used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. All label warnings must be observed until container is commercially cleaned or reconditioned.

### First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs, or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

### Proposition 65

This product contains material listed by the state of California as known to cause cancer, birth defects or other reproductive harm.

### VOC Content

5.4 lbs/gal or 646 g/L, less water and exempt solvents.

**For medical emergencies only,  
call ChemTrec1 (1-800-424-9300).**

**BASF Corporation**  
**Building Systems**

889 Valley Park Drive  
Shakopee, MN, 55379

[www.BuildingSystems.BASF.com](http://www.BuildingSystems.BASF.com)

**Customer Service** 800-433-9517  
**Technical Service** 800-243-6739  
**8.4**



UL  
LISTED  
UL Classified

**LIMITED WARRANTY NOTICE** Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto.** Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND.** BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

**For professional use only. Not for sale to or use by the general public.**

Form No. 1017975 01/12

Printed on recycled paper including 10% post-consumer fiber.

© 2012 BASF

Printed in U.S.A.