

TECHNICAL DATA SHEET

DESCRIPTION

Tuf Seal™ Satin J35S is a scientifically formulated clear, non-yellowing sealer comprised of methyl methacrylate polymers. It dries to a durable, satin finish that not only protects, but also beautifies floors. Tuf Seal™ Satin J35S is designed to provide protection from oil and gasoline and excellent resistance to oils, greases and weathering.

USE

Tuf Seal™ Satin J35S will not only provide improved gasoline/oil resistance, but it will also help to prevent dusting, spalling and inhibit efflorescence. Clean-up time is reduced and simplified since dirt, grease, oil that normally soak into the concrete are easily removed from the coating. Tuf Seal™ Satin J35S not only offers protection for concrete surfaces, but it can also protect and beautify exposed aggregate and stamped concrete.

FEATURES

- Satin finish
- Easy to recoat – No extensive surface preparations
- Resists gasoline, grease, and many oils
- Non-yellowing, clear coating
- Reduces maintenance and clean-up time
- Excellent protection against the weather and ultraviolet radiation
- USDA Approved for incidental food contact

PROPERTIES

Dry time: Approx. 2 hours at 70°F (21°C) for re-coating or light traffic. Wait 12 hours for heavy traffic. Dry time is temperature, humidity and wind dependent.

ESTIMATING GUIDE

Approximate Coverage Rates:

	Sq. Ft/Gal	Sq. M/Liter
1st coat	200 – 300	4.9 – 7.4
2nd coat	400 – 600	9.8 – 14.8

Texture and absorption rate of the concrete will influence coverage rate. Two coats of Tuf Seal™ Satin J35S are recommended. Allow the first coat to dry before applying the second coat.

PACKAGING

ITEM #	PACKAGE	SIZE	
		Gallons	Liters
68078	Unit (36 min.)	1	3.79
68077	Pail	5	18.93
68076	Drum	55	208.20

STORAGE

Store material in a horizontal position to prevent moisture accumulation on the drum head.

Shelf life is 24 months from date of manufacture in unopened containers. Do not store below 0°F (-18°C).

APPLICATION

Surface Preparation: Surface must be clean, dry, free of grease, dirt, paint and efflorescence (white residue). If the substrate is wet from the rain or from surface cleaning, wait a minimum of 24 hours to allow the surface to dry completely before applying. Repair all defects prior to sealing. Protect or avoid spraying Tuf Seal™ Satin J35S on glass or metal.

Mixing: Thoroughly mix the product prior to each use.

Placement: Apply Tuf Seal™ Satin J35S with low pressure spray, roller or brush. Apply uniformly without interruption to prevent streaking. Hold sprayer nozzle perpendicular to the surface and overlap each coat. In order to reduce loss of material to the atmosphere, avoid high pressures when spraying and too fine a spray. Ensure spray nozzle is allowing for a uniform spray pattern without tailings or drips. Coverage will vary with the density and texture of the surface. Apply the Tuf Seal™ Satin J35S to achieve a complete, uninterrupted film. Avoid applications that are too heavy or too light. Heavy coats can bubble and reduce moisture vapor transmission. Too light of an application may not allow material to form a complete film. Avoid application during excessively hot air or substrate temperatures (>90°F, 32.2°C).

CLEAN UP

For tools and equipment use xylol or lacquer thinner.

LIMITATIONS

FOR PROFESSIONAL USE ONLY

For applications of a sealer in an enclosed structure, Dayton Superior recommends a water based product like the Ultra Seal EF.

Sprayers and equipment should have neoprene or viton type hose and gaskets.

Do not apply at temperatures below 40°F (4°C) or when the average daily temperature remains below 40°F (4°C).

Apply to concrete that is a minimum of 7 days old.

Will interfere with the adhesion of sealants, thus avoid spraying Tuf Seal™ Satin J35S into a joint prior to installation of sealant.

Product intended for incidental or short term contact; for long term exposure applications contact Dayton Superior technical services.

Tuf Seal™ Satin J35S will not resist brake or hydraulic fluids.

Concrete Sealer

Sec
11
Sealers

Not for use under resinous (epoxy, polyester, urethane, etc.) coatings.

Film may show black rubber tire marks.

Will darken color of concrete surfaces

PRECAUTIONS

READ MSDS PRIOR TO USING PRODUCT

- Keep material and containers away from high heat, open flames, sparks or other sources of ignition
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (Goggles, Safety Glasses and/or Face Shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 866-329-8724
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.